

SOLVENT BAZLI



Solvent bazlı yapıştırıcılar, yüksek performans gerektiren uygulamalarda güçlü ve kalıcı bağlar oluşturmak amacıyla formüle edilmiştir. Solvent taşıyıcılı sistemler sayesinde, kısa sürede kurur, yüzeye hızlı yapışır ve yüksek yapışma mukavemeti sağlar.

Kullanım Alanları:

Mobilya ve Döşeme: Sünger – kumaş – ahşap – MDF laminasyonları

Otomotiv: Tavan, taban halısı, döşeme ve kaplamaların yapıştırılması

Ayakkabı Sanayi: Saya – taban birleştirme

Yatak Üretimi: Sünger katmanlarının birbirine ve yay sistemlerine yapıştırılması

İzolasyon Malzemeleri: Kauçuk, keçe, ses ve ısı yalıtım panelleri

Avantajları:

Hızlı kuruma ve yüksek ilk tutunma

Uzun ömürlü yapışma

Isı ve nem direnci yüksek formülasyon

Farklı yüzeylerde üstün performans

Sprey uygulamasına uygun

Solvent-Based Adhesives

Solvent-based adhesives are formulated to create strong and permanent bonds in high-performance applications. Thanks to their solvent carrier systems, they dry quickly, adhere rapidly to surfaces, and provide high bonding strength.

Application Areas:

Furniture & Upholstery: Foam – fabric – wood – MDF laminations

Automotive: Bonding of headliners, carpets, trims, and interior linings

Footwear Industry: Upper – sole bonding

Mattress Production: Bonding of foam layers and spring systems

Insulation Materials: Bonding of rubber, felt, sound and thermal insulation panels

Advantages:

Fast drying and high initial tack

Long-lasting adhesion

High resistance to heat and humidity

Superior performance on various surfaces

Suitable for spray application

SOLVENT BAZLI YAPIŞTIRICILAR – YATAK & DÖŞEME SERİSİ (Seri 2)

Ürün	Ambalaj	Açık Kalma Süresi (dk)	Katı Madde (%)	Viskozite	Isı Dayanımı	Yanıcılık	Raf Ömrü	Uygulama Alanları
	Galon / Teneke / Varil / IBC	Tek Yüz / Çift Yüz						
K-35	4 KG / 13 KG / 170 KG / 800 KG	0-5 dk / 0-10 dk	36 ± 2	200 mPa.s ± 50	60-65°C	Yanıcı	12 Ay	Yatak ve döşeme sektöründe yaygın kullanılır
K-70 S	4,6 KG / 15 KG / 225 KG / 1.000 KG	0-5 dk / 0-10 dk	38 ± 2	380 mPa.s ± 50	60-65°C	Yanmaz	12 Ay	Spreyle uygulama için uygun
K-71 S	Aynı	0-5 dk / 0-10 dk	38 ± 2	380 mPa.s ± 50	60-65°C	Yanmaz	12 Ay	Aynı
K-72 C	Aynı	0-3 dk / 0-7 dk	39 ± 2	300 mPa.s ± 50	60-65°C	Yanmaz	12 Ay	Aynı
K-73	Aynı	0-3 dk / 0-7 dk	42 ± 2	520 mPa.s ± 50	60-65°C	Yanıcı	12 Ay	Köpük-köpük, keçe-köpük laminasyonlar
K-76	Aynı	0-2 dk / 0-7 dk	40 ± 2	540 mPa.s ± 50	60-65°C	Yanıcı	12 Ay	Aynı
K-75 F	4 KG / 13 KG / 170 KG / 800 KG	0-5 dk / 0-20 dk	40 ± 2	50 mPa.s ± 10	60-65°C	Yanıcı	12 Ay	İnce püskürtme gerektiren uygulamalar
K-75 NF	4,6 KG / 15 KG / 225 KG / 1.200 KG	0-5 dk / 0-20 dk	40 ± 2	100 mPa.s ± 10	60-65°C	Yanmaz	12 Ay	Yanmaz formülasyon
K-80	Aynı	0-2 dk / 0-7 dk	48 ± 2	580 mPa.s ± 100	60-65°C	Yanıcı	12 Ay	Köpük-keçe-elyaf/dokuma
K-85	Aynı	0-2 dk / 0-7 dk	47 ± 2	560 mPa.s ± 100	60-65°C	Yanıcı	12 Ay	Aynı
K-85 B	Aynı	0-3 dk / 0-12 dk	47 ± 2	570 mPa.s ± 100	60-65°C	Yanıcı	12 Ay	Aynı
K-88	Aynı	0-3 dk / 0-7 dk	39 ± 2	400 mPa.s ± 100	70-75°C	Yanıcı	12 Ay	Yüksek ısı dayanımı gereken uygulamalar

Spreyle uygulanan yapıştırıcılar en çok: Yatak takımı, Şilte, Mobilya, Döşeme endüstrilerinde kullanılır.

Bu malzemeleri yapıştırmak için üretilmiştir:

Ahşap – köpük,
Keçe – keçe,
Keçe – kapitone malzeme,
Keçe – elyaf/dokuma,
Köpük – köpük,
Köpük – kapitone malzeme,
Köpük – keçe – elyaf/dokuma.

- Sprayable adhesives are most commonly used in:
 - Mattress sets
 - Foam panels
 - Furniture
 - Upholstery industry
- Specially developed to bond the following materials:
 - Wood – foam
 - Felt – felt
 - Felt – quilted fabric
 - Felt – nonwoven/fiber
 - Foam – foam
 - Foam – quilted material
 - Foam – felt – nonwoven/fiber

SOLVENT-BASED ADHESIVES – MATTRESS & UPHOLSTERY SERIES (Set 2)

Product	Packaging	Open Time (min)	Solids (%)	Viscosity	Heat Resistance	Flammability	Shelf Life	Application Areas	
	Gallon / Can / Drum / IBC	Single Side / Double Side							
K-35	4 KG / 13 KG / 170 KG / 800 KG	0-5 / 0-10 min	36 ± 2	200 mPa.s ± 50	60-65°C	Flammable	12 mo	Widely used in mattress and upholstery sector	
K-70 S	4.6 KG / 15 KG / 225 KG / 1,000 KG	0-5 / 0-10 min	38 ± 2	380 mPa.s ± 50	60-65°C	Non-Flammable	12 mo	Suitable for spray application	
K-71 S	Same as above	0-5 / 0-10 min	38 ± 2	380 mPa.s ± 50	60-65°C	Non-Flammable	12 mo	Same as above	
K-72 C	Same as above	0-3 / 0-7 min	39 ± 2	300 mPa.s ± 50	60-65°C	Non-Flammable	12 mo	Same as above	
K-73	Same as above	0-3 / 0-7 min	42 ± 2	520 mPa.s ± 50	60-65°C	Flammable	12 mo	Foam-to-foam, felt-to-foam bonding	
K-76	Same as above	0-2 / 0-7 min	40 ± 2	540 mPa.s ± 50	60-65°C	Flammable	12 mo	Same as above	
K-75 F	4 KG / 13 KG / 170 KG / 800 KG	0-5 / 0-20 min	40 ± 2	50 mPa.s ± 10	60-65°C	Flammable	12 mo	Suitable for fine spray application	
K-75 NF	4.6 KG / 15 KG / 225 KG / 1,200 KG	0-5 / 0-20 min	40 ± 2	100 mPa.s ± 10	60-65°C	Non-Flammable	12 mo	Non-flammable formulation	
K-80	Same as above	0-2 / 0-7 min	48 ± 2	580 mPa.s ± 100	60-65°C	Flammable	12 mo	Foam – felt – fabric lamination	
K-85	Same as above	0-2 / 0-7 min	47 ± 2	560 mPa.s ± 100	60-65°C	Flammable	12 mo	Same as above	
K-85 B	Same as above	0-3 / 0-12 min	47 ± 2	570 mPa.s ± 100	60-65°C	Flammable	12 mo	Same as above	
K-88	Same as above	0-3 / 0-7 min	39 ± 2	400 mPa.s ± 100	70-75°C	Flammable	12 mo	Designed for high heat resistance applications	

